

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A61L 25/00, A61F 5/443, C09J 123/20	A1	(11) International Publication Number: WO 99/11302 (43) International Publication Date: 11 March 1999 (11.03.99)
(21) International Application Number: PCT/DK98/00368 (22) International Filing Date: 27 August 1998 (27.08.98) (30) Priority Data: 0993/97 29 August 1997 (29.08.97) DK (71) Applicant (for all designated States except US): COLOPLAST A/S [DK/DK]; Høltedam 1, DK-3050 Humlebæk (DK). (72) Inventors; and (75) Inventors/Applicants (for US only): CHEN, Fei [DK/DK]; Gjerdesager 15, DK-3540 Lynge (DK). CIOK, Danuta [PL/DK]; Violens Kvarter 8, DK-2990 Nivaa (DK). (74) Common Representative: COLOPLAST A/S; Patent Dept., Høltedam 1, DK-3050 Humleback (DK).		(81) Designated States: AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), EE, EE (Utility model), ES, FI, FI (Utility model), GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published With international search report.
(54) Title: A PRESSURE SENSITIVE ADHESIVE COMPOSITION (57) Abstract A pressure sensitive adhesive composition suitable for medical purposes comprising a rubbery elastomeric base and one or more water soluble or water swellable hydrocolloids, said adhesive composition comprising a substantially homogeneous mixture of 25-60 % of one or more polybutenes, 3-35 % of one or more styrene copolymers, and 20-60 % of one or more hydrocolloids shows very good properties as an adhesive for ostomy appliances.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

TITLE

A Pressure Sensitive Adhesive Composition.

FIELD OF THE INVENTION

The present invention relates to pressure sensitive adhesive compositions suitable for various medical applications and especially suitable for use for adhesion to the skin, in particular in the field of ostomy care. More specifically, this invention relates to adhesive compositions comprising a rubbery elastomeric base and one or more water soluble or water swellable hydrocolloids are dispersed therein, the use of such adhesive compositions for the preparation of a wound dressing or an adhesive wafer for an ostomy appliance, and to wound dressings or ostomy appliances comprising such adhesive composition.

BACKGROUND OF THE INVENTION

Various skin adhesive agents are used today for the above mentioned purposes.

A very widespread embodiment of skin adhesive agents comprises a self-adhesive elastomeric matrix, in which water-absorbing, swelling particles, the so-called hydrocolloids, are dispersed.

Adhesive compositions comprising hydrocolloids have been known for many years. US. patent No. 3,339,549 discloses a blend of a rubbery elastomer such as polyisobutylene and one or more water soluble or water swellable hydrocolloids such as a powdery mixture of pectin, gelatine and carboxymethylcellulose.

The adhesive mass has a water-insoluble film applied to one surface. A composition of this type is available commercially from E.R. Squibb & Sons Inc. under the trademark "Stomadhesive" and is used as a skin barrier around stomas to prevent skin breakdown by the corrosive fluids discharged by the stoma.

In adhesive compositions of this type, the polyisobutylene is responsible for provision of the adhesive properties and the dispersed hydrocolloid powders absorb fluid and render the adhesive agent capable of also adhering to moist skin (wet

tack). These compositions are also gaining increasing acceptance as wound dressings for dermal ulcers, burns and other exuding wounds.

One major problem which has been encountered with conventional adhesive compositions comprising hydrocolloids is their susceptibility to breakdown upon exposure to body fluids. When the compositions are used as skin barriers, e.g., around stomas, absorption of fluid is desirable, but excessive swelling causes the composition to lose its integrity opening for leaks and the barrier must be replaced more often than is desirable from a skin protection point of view, and very often, a residue remains on the skin, which in many cases is difficult to remove.

10 A number of attempts have been made to improve the properties of adhesive compositions in order to overcome the above-mentioned drawbacks.

US. Patent Nos. 4,192,785 and 4,551,490 describe incorporating into an adhesive composition of a cohesive strengthening agent such as a natural or synthetic fibrous material, finely divided cellulose, cross-linked dextran, cross-linked carboxymethylcellulose or a starch-acrylonitrile graft copolymer. The cohesive strengthening agent is stated to control the rate of hydration of the composition thereby increasing the resistance against breakdown by body fluids.

US. Patent No. 4,477,325 describes incorporation of a mixture of a copolymer resin of ethylene and vinyl acetate (EVA) into the adhesive composition. After mixing and moulding, the composition is subjected to ionising radiation to form a cross-linked polymer network of the EVA or comprising EVA and another cross-linked resin. The cross-linked matrix is said to provide a controlled swelling.

US. Patent No. 4,496,357 describes the incorporation of fumed silica into adhesive compositions to control swelling.

25 EP No. 0 122 344 B1 describes incorporation of one or more natural or synthetic polymers capable of developing elastomeric properties when hydrated, such as gluten and long chain polymers of methyl vinyl ether/maleic acid, into the

adhesive composition. The adhesive composition is stated to be resistant to erosion by moisture and body fluids.

EP patent No. 0 340 945 B1 describes incorporation of some polycationic hydrocolloid particles into a hydrocolloid composition. The mixture of polycationic, poly-
5 anionic and neutral hydrocolloids is stated to provide increased integrity without a concomitant decrease in absorbing capacity.

In other embodiments, styrene copolymers have been incorporated which is disclosed in a number of patent references.

In US Patent No. 4,231,369 Sorensen et al. disclose an ostomy skin barrier consisting of a styrene copolymer having dispersed therein a water soluble hydrocolloid gum and a tackifier.

In US Patent No. 4,367,732 Poulsen et al. disclose an ostomy skin barrier consisting of a water soluble hydrocolloid dispersed in a continuous phase consisting of a styrene copolymer, a hydrocarbon tackifier, and a plasticizer, an antioxidant,
15 and an oily extender.

US Patent No. 4,551,490 (Doyle et al.) discloses medical grade pressure sensitive adhesive compositions comprising a homogeneous mixture of 5-30% of one or more polyisobutylenes, 3-20% of one or more styrene radial or block type copolymers, mineral oil, one or more water soluble hydrocolloid gums, and a tackifier. One or more water swellable cohesive strengthening agents, an antioxidant,
20 and various other optional ingredients also may be included within the adhesive composition.

EP patent publication No. 81907 discloses an ostomy appliance comprising a skin barrier (A) surrounding the stoma and a coupling element (B) including an
25 outwardly extending flange permanently affixed to the skin barrier (A) and a microporous adhesive layer (C) having an upper porous layer. The skin barrier adhesive (A) comprises a homogeneous 30-70% of a blend of low molecular weight

polyisobutylene and one or more optional thermoplastic elastomers selected from medium molecular weight polyisobutylene, butyl rubber, and styrene isoprene copolymers and having dispersed therein 35-65% of one or more water soluble hydrocolloids and one or more water swellable or inert cohesive strength-
5 ening agents.

Generally speaking, these prior methods are superior to improve the integrity of adhesive compositions. Nevertheless, need still exists for better adhesive composition having resistance to biological fluids as well as the properties of improved adhesion to the skin and stretchability.

10 Now it has been found that an improved adhesive composition having resistance to biological fluids as well as the properties of improved adhesion to the skin and stretchability may be obtained.

BRIEF DESCRIPTION OF THE INVENTION

The present invention relates to a pressure sensitive adhesive composition suitable for various medical applications and especially suitable for use for adhesion to the skin, in particular in the field of ostomy care. More specifically, this invention relates to adhesive compositions comprising a rubbery elastomeric base and one or more water soluble or water swellable hydrocolloids are dispersed, ostomy appliances comprising such adhesive compositions and the use of such adhesive compositions for preparing wound dressings or ostomy appliances.
20

DETAILED DESCRIPTION OF THE INVENTION

The present invention relates to a pressure sensitive adhesive composition suitable for medical purposes comprising a rubbery elastomeric base and one or more water soluble or water swellable hydrocolloids, said adhesive composition comprising a substantially homogeneous mixture of 25 - 60 % of one or more polybutenes, 3 - 35% of one or more styrene copolymers, and 20 - 60% of one or more hydrocolloids.
25

Without limiting the invention to any hypothesis it is believed that the combination of the styrene radial or block copolymer component and one or more polybutenes in the proportions stated above provides extensibility and both rapid and complete recovery from modular strains to the composition. The combination of
5 the adhesive properties of the polybutenes and the absorbing properties of the hydrocolloids renders the adhesive composition of the invention especially suitable for use in ostomy appliances.

It is preferred that the styrene copolymer is a styrene-butadiene-styrene block copolymer or a styrene-isoprene-styrene block copolymer. Preferably, one or
10 more styrene-isoprene-styrene (SIS) block type copolymers are employed.

The amount of styrene block-copolymer is preferably from 5 to 20% of the total adhesive composition.

The butene component is suitably a conjugated butadiene polymer selected from polybutadiene and polyisoprene.

15 The Flory molecular weight of the polybutenes to be used according to the invention is preferably from 50,000 to 60,000.

The polybutenes are preferably present in an amount of from 35 - 50% of the total adhesive composition.

Suitable hydrocolloids for incorporation in the adhesive compositions of the in-
20 vention are selected from naturally occurring hydrocolloids, semisynthetic hydrocolloids and synthetic hydrocolloids.

More particularly, the hydrocolloids are preferably selected from guar gum, locust bean gum (LBG), pectin, alginates, gelatine, xanthan and/or gum karaya; cellulose derivatives (e.g. salts of carboxymethylcellulose such as sodium

carboxymethylcellulose, methylcellulose and hydroxypropylmethylcellulose) and/or sodium starch glycolate and/or polyvinylalcohol and/or polyethylene glycol.

It is preferred to use a combination of two or more hydrocolloids. It is especially preferred to use a combination of pectin, gelatine and carboxymethylcellulose as the hydrocolloid component.

The total amount of hydrocolloids is preferably 30 - 50% of the total composition.

An especially preferred composition according to the invention comprises 50% of a mixture of polyisobutylene and SIS and 50% of a mixture of hydrocolloids comprising gelatine, pectin and CMC.

In a preferred embodiment of the invention for use in an ostomy appliance, the adhesive composition the adhesive component in a "Swiss roll" adhesive of the kind disclosed in WO 89/05619, the other, more absorbing, component e.g. comprising a mixture of PIB and a hydrocolloid or any other suitable adhesive.

15 In a further aspect, the invention relates to the use of an adhesive composition comprising a rubbery elastomeric base and one or more water soluble or water swellable hydrocolloids, said adhesive composition comprising a substantially homogeneous mixture of 25 - 60 % of one or more polybutenes, 3 - 35% of one or more styrene copolymers, and 20 - 60% of one or more hydrocolloids for securing 20 ing ostomy appliances to the skin and for sealing around an ostomy, for securing wound dressings or wound drainage bandages to the skin, for securing devices for collecting urine to the skin, or for securing orthoses or prostheses to the skin.

In a still further aspect, the invention relates to an ostomy appliance for placing on the abdomen of a patient for use in collecting discharge of visceral contents 25 comprising an adhesive composition containing a rubbery elastomeric base and one or more water soluble or water swellable hydrocolloids, said adhesive composition comprising a substantially homogeneous mixture of 25 - 60 % of one or

more polybutenes, 3 - 35% of one or more styrene copolymers, and 20 - 60% of one or more hydrocolloids.

The ostomy appliance according to the invention may be an open or a closed appliance suitable for use in connection with a colostomy, an ileostomy or a uros-
5 tomy. It may be a one-piece appliance or a body side member or face plate forming part of a two-piece appliance comprising the body side ostomy member and a separate collection bag. A separate collection bag may be attached to the body side member in any convenient manner known per se, e.g. via a coupling ring or by a flange covered with an adhesive.

- 10 An ostomy appliance according to the invention may be made from materials conventionally used for the preparation of ostomy appliances in a manner known per se in the field.

The invention is illustrated more in detail in the below Examples disclosing embodiments of the invention.

15 MATERIALS AND METHODS

PIB: Polyisobutylene available under the trademark Vistanex from Exxon Chemical Co. as grade LM-MH.

Kraton D1107: Styrene-isoprene-styrene copolymer having a molecular weight of 212,000-260,000 (GPC) and a content of diblock 15-25%.

- 20 Gelatine: Gelatine P.S.98.240.233 available from ED. Geistlich Sohne AG.

Pectin: Pectin LM 12CG Z or Pectin USP/100 from Copenhagen Pectin A/S.

CMC: Sodium carboxymethylcellulose available from Akzo under the tradename Akucell® AF2881 or from Hercules Corp. under the trademark Blanose® 9H4XF.

A Z mixer Type LKB 025 from Herman-Linden was used.

EXPERIMENTAL PART

Example 1

Preparation of an adhesive material according to the invention

An adhesive composition having the composition stated in the below table 1 was produced.

Table 1

Ingredient	Percent by weight
PIB	41,5
Kraton D1107 (SIS)	8,5
Gelatine	17,5
Pectin	10
CMC	22,5

100 grams of PIB was added to a Z mixer at 150 °C and softened for 5 minutes. Then 100 grams of Kraton® D1107 was added and mixing was continued at 150 °C and 50 mbar until the blend was homogeneous. The mass was cooled to 80 °C, and 166 grams of the mass was removed from the mixer. To the remaining mass was added 66 grams of PIB, 35 grams of gelatine, 20 grams of pectin and 45 grams of CMC. Mixing is continued under 80 °C and 50 mbar until a homogeneous dough-like mixture was obtained.

While still hot and soft, the resulting dough-like mass was then removed from the 15 mixer and formed into sheet stock material having a thickness of approximately 1 mm by compression moulding the adhesive mass at approximately 90 °C and 100 Bar between two sheets of silicone release paper. The resultant flat plate was then cut into pieces having the desired shapes.

The adhesive composition may be used for securing ostomy appliances to the 20 skin and for sealing around an ostomy, for securing wound dressings or wound drainage bandages to the skin, for securing devices for collecting urine to the

skin , or for securing orthoses or prostheses to the skin. The ostomy appliances or wound dressings may be any such product known per se and may be prepared in a manner analogous to the preparation of similar products using conventional adhesive compositions.

5 Examples 2 - 9

Following the procedure of Example 1 adhesive compositions having the compositions stated in the below tables 2 and 3 were prepared.

Table 2

Ingredient	Example 2	Example 3	Example 4	Example 5
PIB	40	45	35	50
Kraton® D1107	10	5	15	10
Gelatine	17,5	17,5	17,5	10
Pectin pomosin	10	10	10	20
CMC	22,5	22,5	22,5	10

Table 3

Ingredient	Example 6	Example 7	Example 8	Example 9
PIB	50	42,5	37,5	45
Kraton® D1107	20	12,5	17,5	15
Gelatine	10	15	15	10
Pectin pomosin	10	15	15	10
CMC	10	15	15	20

Example 10

Comparison of colostomy bags having an adhesive wafer comprising an adhesive according to the invention with commercially available bags.

5 In an open, multi centre, cross-over clinical trial Naturess ostomy bag (ConvaTec) and 1 piece Dansac Light ostomy bag (Dansac A/S) were compared with colostomy bags having an adhesive wafer comprising an adhesive according to the invention having the composition as stated in Example 2 with the purpose to compare the performance of the adhesive.

10 Inclusion criteria

The following test persons were eligible for inclusion into the study:

Colostomists who for at least 1 month had been discharged from hospital and were:

More than 18 years of age.

Capable of giving written informed consent.

Able to complete the registration forms.

In good general health

15

Exclusion criteria

The following were ineligible for inclusion into the study:

Colostomists with severe skin problems and undergoing treatment.

Colostomists who were pregnant or breast feeding.

5 The following parameters were evaluated:

Wear time, reason for removal, and the immediate adhesion, Flexibility, Pain at removal, Residues - outer section, and Residues - inner section according to a scale 1 - 5, where 5 is best:

In connection with application of the adhesive the immediate adhesion to the skin
10 was rated as:

The immediate adhesion to the skin and flexibility were rated as:

5 = Excellent

4 = Moderate

3 = Acceptable

15 2 = Poor

1 = Very poor

The pain at removal, the residues on skin from the outer section of the adhesive
and the residues on skin around the stoma from the inner section of the adhesive

20 were rated as:

5 = Not at all

4 = A little

3 = Acceptable

2 = Some

25 1 = Very much

The results are summarised in the below Tables 4 and 5.

Table 4

Comparison of adhesive according to the invention with adhesive of Naturess ostomy bag (in total 67 ostomates).

Efficacy Parameter	Bag with adhesive according to invention	Naturess ostomy bag	P-value
The weartime	12.79 hours	12.82 hours	0.941
The reason for removal			
Usual routine	29.4%	22.9%	0.039*
Hygiene	58.4%	52.9%	0.497
Leakage under adhesive	8.1%	8.4%	0.766
Adhesive partly not sticking	6.3%	6.7%	0.888
Adhesive not sticking at all	0.4%	0.2%	0.564
Skin irritation	4.3%	12.7%	0.027
The immediate adhesion	4.16	3.52	0.00007*
Flexibility	4.25	3.82	0.0003*
Pain at removal	4.74	4.29	0.001*
Residues - outer section	4.79	4.55	0.021*
Residues -around stoma	4.82	4.51	0.003*

* Significant difference ($\alpha = 0.05$) in the Friedman test or in the Wilcoxon signed

5 Rank test

% is in % of all used bags

Table 5

Comparison of adhesive according to the invention with adhesive of 1 piece Dansac Light ostomy bag (in total 80 ostomates).

Efficacy Parameter	Bag with adhesive according to invention	1 piece Dansac Light ostomy bag	P-value
The weartime	10.88 hours	10.11 hours	0.101
The reason for removal			
Usual routine	62.0%	54.3%	0.035*
Hygiene	43.1%	46.4%	0.434
Leakage under adhesive	4.0%	5.3%	0.574
Adhesive partly not sticking	4%	7.4%	0.203
Adhesive not sticking at all	0.5%	0.2%	0.655
Skin irritation	1.1%	4.3%	0.127
The immediate adhesion	4.38	4.14	0.041*
Flexibility	4.20	4.16	0.741
Pain at removal	4.71	4.00	0.00003*
Residues - outer section	4.70	4.23	0.001*
Residues - around stoma	4.77	4.48	0.011*

* Significant difference ($\alpha = 0.05$) in the Friedman test or in the Wilcoxon signed

5 Rank test

% is in % of all used bags

Conclusion

For the adhesive according to the invention it is noticed that the adhesive has a better immediate adhesion, it resists the wash out both at the inner and the outer edge and still it is less painful to remove than the known products. These differences are statistically significant.

No significant difference was found concerning the weartime.

For the reason to change, a significant difference was found for "usual routine" in favour of the bags having the adhesive according to the invention. Thus, a bag according to the invention can remain on the skin as long as the ostomate wishes.

No significant difference was found concerning the flexibility, between the adhesive of the bag of the invention and the Dansac bag whereas the adhesive of the bag of the invention was more flexible than the adhesive on the Naturess bag

CLAIMS

1. A pressure sensitive adhesive composition suitable for medical purposes comprising a rubbery elastomeric base and one or more water soluble or water swellable hydrocolloids, said adhesive composition comprising a substantially homogeneous mixture of 25 - 60 % of one or more polybutenes, 3 - 35% of one or more styrene copolymers, and 20 - 60% of one or more hydrocolloids.
2. An adhesive composition as claimed in claim 1 wherein the styrene copolymer is a styrene-butadiene-styrene block copolymer or a styrene-isoprene-styrene block copolymer.
3. An adhesive composition as claimed in claim 2 wherein the styrene copolymer is a styrene-isoprene-styrene block copolymer.
4. An adhesive composition as claimed in any of claims 1 - 3 wherein the butenes is a conjugated butadiene polymer selected from polybutadiene and polyisoprene.
5. An adhesive composition as claimed in any of claims 1 - 4 wherein the hydrocolloids are selected from naturally occurring hydrocolloids, semisynthetic hydrocolloids and synthetic hydrocolloids.
6. An adhesive composition as claimed in claim 5 wherein the hydrocolloids are selected from guar gum, locust bean gum (LBG), pectin, alginates, gelatine, xanthan and/or gum karaya; cellulose derivatives (e.g. salts of carboxymethylcellulose such as sodium carboxymethylcellulose, methylcellulose and hydroxypropylmethylcellulose) and/or sodium starch glycolate and/or polyvinylalcohol and/or polyethylene glycol.
7. An ostomy appliance for placing on the abdomen of a patient for use in collecting discharge of visceral contents comprising an adhesive composition

containing a rubbery elastomeric base and one or more water soluble or water swellable hydrocolloids, said adhesive composition comprising a substantially homogeneous mixture of 25 - 60 % of one or more polybutenes, 3 - 35% of one or more styrene copolymers, and 20 - 60% of one or more hydrocolloids.

- 5 8. Use of an adhesive composition comprising a rubbery elastomeric base and one or more water soluble or water swellable hydrocolloids, said adhesive composition comprising a substantially homogeneous mixture of 25 - 60 % of one or more polybutenes, 3 - 35% of one or more styrene copolymers, and 20 - 60% of one or more hydrocolloids for securing ostomy appliances to the skin and for
10 sealing around an ostomy, for securing wound dressings or wound drainage bandages to the skin, for securing devices for collecting urine to the skin , or for securing orthoses or prostheses to the skin.

INTERNATIONAL SEARCH REPORT

International application No.

PCT/DK 98/00368

A. CLASSIFICATION OF SUBJECT MATTER		
IPC6: A61L 25/00, A61F 5/443, C09J 123/20 According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED		
Minimum documentation searched (classification system followed by classification symbols)		
IPC6: A61L, A61F, C09J		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
SE,DK,FI,NO classes as above		
Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)		
WPI, CAPLUS		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GB 2300195 A (ALCARE CO LTD), 30 October 1996 (30.10.96), page 6 - page 8, claims 1-6 --	1-8
X	US 4551490 A (ARTHUR DOYLE ET AL), 5 November 1985 (05.11.85), column 2, line 65 - column 4, line 16, claims --	1-8
A	US 5492943 A (EMIL STEMPEL), 20 February 1996 (20.02.96), column 3, line 61 - column 4, line 48, claims --	1-8
<input checked="" type="checkbox"/> Further documents are listed in the continuation of Box C. <input checked="" type="checkbox"/> See patent family annex.		
* Special categories of cited documents: "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art "&" document member of the same patent family		
Date of the actual completion of the international search		Date of mailing of the international search report
2 December 1998		04-12-1998
Name and mailing address of the ISA/ Swedish Patent Office Box 5055, S-102 42 STOCKHOLM Facsimile No. +46 8 666 02 86		Authorized officer Barbro Nilsson Telephone No. +46 8 782 25 00

INTERNATIONAL SEARCH REPORT
Information on patent family members

03/11/98

International application No.

PCT/DK 98/00368

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 2300195 A	30/10/96	CA 2174836 A DE 19616563 A GB 9608331 D JP 8294528 A	27/10/96 31/10/96 00/00/00 12/11/96
US 4551490 A	05/11/85	AU 578612 B AU 2950184 A CA 1225764 A DD 223459 A DE 3473731 A DK 163211 B,C DK 311384 A EP 0130061 A,B SE 0130061 T3 IE 58125 B JP 1970283 C JP 6078507 B JP 60020976 A	03/11/88 10/01/85 18/08/87 12/06/85 06/10/88 10/02/92 28/12/84 02/01/85 14/07/93 18/09/95 05/10/94 02/02/85
US 5492943 A	20/02/96	AU 1796295 A JP 8000722 A NZ 272236 A	04/01/96 09/01/96 26/04/96
EP 0081907 A1	22/06/83	SE 0081907 T3 AT 19943 T AU 567864 B AU 9016182 A CA 1187368 A DK 159641 B,C DK 186590 A DK 529082 A IE 54788 B JP 1677888 C JP 3041178 B JP 58103452 A US 4775374 A ZA 8207903 A	15/06/86 10/12/87 02/06/83 21/05/85 12/11/90 03/08/90 28/05/83 14/02/90 13/07/92 21/06/91 20/06/83 04/10/88 31/08/83